

**YOUR BEST TILING  
WORK** WITH **BAMBURI  
SETI TILE ADHESIVE**



**Good  
Strength**



**Meets Kenyan (KS 1530)  
and European (EN 12004)  
performance standards**



**Economical**



**Suitable for  
interior wall and  
floor tiling works**



**Bamburi  
cement**

**Part of you. From the start**

**TectorCeram SETI 300**

**TILE ADHESIVE**

Bamburi's **TectorCeram SETI 300** is a cementitious tile adhesive specially formulated using Portland cement, uniquely selected additives and polymers with specially graded fine aggregates, to give it unique performance attributes ideal for the intended application.

## 1. KEY ATTRIBUTES

- Comes ready to use (only add water as advised)
- Enhanced bonding attributes compared to conventional cement paste
- Faster application due to good spreadability
- Excellent high strength and water retention properties
- Suitable for fixing small to medium sized ceramic tiles on walls and floors

## 2. ADVANTAGES

- A high quality and easy to store premixed powder
- Superior grip
- Excellent workability
- Higher productivity and saves time
- Smooth finish

## 3. APPLICATIONS



*Internal tiling on walls*



*Internal tiling on floors*



*Tile repairs and rehabilitation works*

# USING TectorCeram SETI 300

## 1. SURFACE PREPARATION

Substrate should be structurally sound, clean and free of any contaminants that may reduce or prevent proper adhesion.

Clean the surface to remove dust and dirt, loose particles, grease and any traces of foreign material using wire brush and sand paper.



## 2. MIXING

a. Take about 6 – 7 litres of clean water for use with 25 kgs of **TectorCeram SETI 300**

b. Mix **TectorCeram SETI 300** with water to achieve the required/right consistency ( should have a creamy consistency)

c. Allow the mix to stand for about 5 – 10 minutes and then mix again before applying



## 3. APPLICATION

a. Dampen the surface with clean water (wipe out or allow excess water to drain off)

c. Place the tile in place and tap gently with wooden hammer

b. Apply mixed **TectorCeram SETI 300** using a notched trowel to a thickness of about 2 – 3mm

d. Remove excess substrate from the tile using a damp cloth

## 4. PRECAUTIONS

**TectorCeram SETI 300** is non-toxic. However, being a cementitious material, avoid eye and prolonged skin contact. It is recommended to use protective gloves, dust masks and goggles during handling.

### PACKAGING



### STORAGE



### SHELF LIFE



## 5. TECHNICAL DATA

Type	Powder
Color	Grey
Open time	10 – 20 minutes
Pot time	120 – 180 minutes
Water Demand	6 – 7 litres/25kg Powder
Workability	Excellent



**Call our  
Customer Service Team  
+254 722 202 941**

**[www.lafarge.co.ke](http://www.lafarge.co.ke)**



Bamburi Cement

